

**PCT**WORLD INTELLECTUAL PROPER  
International Bur.

INTERNATIONAL APPLICATION PUBLISHED UNDER


WO 9606961A1

<b>(51) International Patent Classification 6 :</b> <b>C30B 29/00, B32B 9/00, 19/00, A47G 35/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 96/06961</b> <b>(43) International Publication Date:</b> 7 March 1996 (07.03.96)
<b>(21) International Application Number:</b> PCT/US95/10379 <b>(22) International Filing Date:</b> 14 August 1995 (14.08.95)  <b>(30) Priority Data:</b> 08/296,779                      26 August 1994 (26.08.94)                      US  <b>(71) Applicant:</b> DEPOSITION SCIENCES, INC. [US/US]; 386 Tesconi Court, Santa Rosa, CA 95401 (US).  <b>(72) Inventor:</b> ROGERS, Donald, Z.; 3230 Hidden Valley Drive, Santa Rosa, CA 95404 (US).  <b>(74) Agents:</b> WITTENBERG, Malcolm, B. et al.; Crosby, Heafey, Roach & May, 1999 Harrison Street, Oakland, CA 94612 (US).		<b>(81) Designated States:</b> CA, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>

**(54) Title:** NOVEL GEMSTONES AND DECORATIVE OBJECTS COMPRISING A SUBSTRATE AND AN OPTICAL INTERFERENCE FILM

**(57) Abstract**

An article useful as a gemstone or decorative object comprising a formed substrate (1) used as a base for an optical interference coating (2) applied on the exterior of the substrate (1). The optical interference coating (2) is made of alternating layers of materials with relatively high refractive indices and relatively low refractive indices; the refractive indices and thickness of the alternating layers being chosen so that at least part of the light of wavelengths between 400 nanometers and 700 nanometers incident on the article is reflected. The optical interference coating (2) creates an interference filter formed of alternating layers of a material with a low refractive index and a material with a high refractive index. The article provides a visual appearance that is novel and different from other gemstones or decorative objects, either man-made or natural.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

WO 96/06961

PCT/US95/10379

-1-

5

**NOVEL GEMSTONES AND DECORATIVE OBJECTS COMPRISING  
A SUBSTRATE AND AN OPTICAL INTERFERENCE FILM**

10

**TECHNICAL FIELD OF THE INVENTION**

The present invention involves decorative articles in the form of gemstones and decorative objects in the form of a substrate and optical interference coatings so that at least part of the light of wavelengths between 400 nanometers and 700 nanometers incident on the article is reflected.

15

**BACKGROUND OF THE INVENTION**

20

25

30

The art of producing gemstones for use in jewelry and other decorative objects by cutting and polishing naturally occurring mineral deposits is an ancient one. Existing gemstones that are colored achieve the color by absorbing some of the incident visual light. The absorption is often due to impurities in an otherwise transparent material such as aluminum oxide. Other natural gemstones, such as diamonds, are intrinsically colorless, but achieve high sparkle and flashes of color by the refraction induced by the high refractive index of the material. All intrinsically colored existing gemstones achieve their perceived color by preferential absorption of some of the wavelengths of light in the range of 400 nanometers to 700 nanometers. By the term intrinsically colored is meant colors that are invariant with respect to viewing angle, and are not the result of refraction of the incident light.

35

40

In modern times various synthetic and enhanced gemstones have been manufactured by a variety of processes. Some of these processes are intended to produce copies of naturally occurring gemstones, or to enhance the color of otherwise less valuable gemstones. For example, exposure of some transparent, colorless minerals to various types of high energy radiation can cause the mineral to become absorbing and therefore colored. Alternately, various processes have been described to improve the durability of

WO 96/06961

PCT/US95/10379

-2-

gemstones by applying an overcoat of a more durable material. For example, Mayer (US 3,539,379) describes the deposition of a single layer of aluminum oxide to the exterior of a gemstone to improve hardness and scratch resistance, but with the specific additional intent of not changing the perceived color of the native gemstone. German patent DE 3708171 A1 and a German patent application describe the deposition of diamond like coating to improve the hardness of gemstones. Feller (US 4,599,251) discloses a decorative object manufactured by forming a single layer of a metal oxide on a silicon surface. Neumiller (US 4,793,864) discloses formation of an organic film on the surface of a gemstone for the purpose of protecting the gemstone against ultraviolet and infrared radiation, and for the purpose of cleaning the surface of the gemstone. The modification of a gemstone by deposition of one or more layers on the upper surfaces only is described in Austrian Patent 265718 (1968), Swiss Patent 410,498 (1961), and Swiss Patent 346,666 (1956).

Whether natural or synthetic, all prior art gemstones that are perceived as colored by the eye achieve the color by absorption of some of the incident light, (except for intrinsically colorless gems, such as diamonds, whose perceived colors are due to refraction at the surface of the stone). When light strikes the surface of such a colored gemstone, some portion of the incident light is reflected, and the remainder of the light is transmitted into the interior of the gemstone. Because all wavelengths of the incident light are reflected in substantially equal amounts, the reflected light has no perceived color other than that of the original incident light. Some wavelengths of the incident light that is transmitted into the interior of the gemstone are absorbed by the material of the gemstone. Those wavelengths of light not absorbed by the gemstone eventually pass out of the gemstone. Because the light that has passed through the gemstone is now deficient in certain wavelengths of light (compared to the light incident on the gemstone) the gemstone appears to the observer to have a color, said color being that produced by the complement of the wavelengths of light absorbed by the gemstone.

It is a further property of all prior art colored gemstones that the perceived color is invariant with the angle of incidence of light or of the position of the observer with respect to the gemstone with the

WO 96/06961

PCT/US95/10379

-3-

exception of refraction affects as described above. Thus all prior art colored gemstones are monochromatic in that the light reflected from the surface of the gemstone is not colored, and the perceived color of the light transmitted through the gemstone is invariant with the angle of incidence of the light or the position of the observer.

It is a further property of all prior art colored gemstones that the perceived brilliance of the gemstone is less than that of a colorless gemstone such as a diamond. This lesser brilliance is an unavoidable result of the fact that the color of the gemstone is produced by absorption of a large fraction of the total incident visible light. Thus less total visible light is returned to the eye from a colored gemstone than from a colorless gemstone of the same size and cut. The lesser amount of total visible light leads to the colored gemstone as being perceived as of lower brilliance, or duller, than the corresponding colorless gemstone.

It would be of great advantage to provide colored gemstones with a perceived brilliance as high as that of a colorless gemstone. It would be of further advantage to have such a colored gemstone be polychromatic, and for the perceived color to be dependent on the angle of incidence of the illumination source.

It is a natural property of existing colored gemstones that the depth of color of a small stone is less than the depth of color of a larger stone of the same material and cut. This is a consequence of the fact that the path length of the light in the small stone is less than in the large stone, and by Beer's Law the amount of light absorbed in the smaller stone is less. Because for reasons of economy it is often desired to use very small gemstones in jewelry, the lesser depth of color of such small stones is a disadvantage. It would be of great advantage to provide colored gemstones in which small samples had the same depth of color as larger samples.

An object of the present invention is providing colored gemstones and decorative objects whose perceived color is polychromatic, and whose perceived brilliance is greater than that of prior art colored gemstones.

Another object of the present invention is providing colored gemstones and decorative objects whose perceived color is dependent

WO 96/06961

PCT/US95/10379

-4-

on the angle of illumination and the position of the observer with respect to the gemstone or object.

5 Yet another object of the present invention is providing colored gemstones in which small stones have the same perceived depth of color as larger stones made of the same material.

Yet another object of the present invention is providing decorative objects of novel and beautiful appearance.

10 Additional objects and features of the invention will be made evident by the following description in which the preferred embodiments are set forth in detail in conjunction with the accompanying drawings.

#### BRIEF DESCRIPTION OF THE DRAWINGS

15 FIGURE 1 is a cross-sectional representation of a faceted substrate bearing an optical interference film on its external surface, where 1 is the substrate material and 2 is the optical interference coating.

FIGURE 2 is a cross-sectional view of a small section of the substrate surface together with the multi-layer optical interference film, where 3 is the substrate material, 4 is one component in the interference film, and 5 is the other component of the interference film.

20 FIGURE 3 is a graphic representation of the reflection spectrum in the visual range of an example interference coating of the type used in the present invention, and further described in EXAMPLE 1.

25 FIGURE 4 is a graphic representation of the reflection spectrum in the visual range of an example interference coating of the type used in the present invention, and further described in EXAMPLE 2.

#### SUMMARY OF THE INVENTION

30 In accordance with this invention, an object, previously formed to the desired final shape, hereinafter referred to as a substrate, is supplied with a thin film coating over substantially the entire surface of the substrate. This thin film coating consists of alternating layers of materials with relatively high refractive index and relatively low refractive index, the thickness of the layers being chosen so that the  
35 coating as a whole forms an interference filter such that the coating reflects a substantial portion of incident light of wavelengths between 400 nanometers and 700 nanometers (hereinafter referred to as visible

WO 96/06961

PCT/US95/10379

-5-

light), inclusive. In the preferred implementation of the invention, the materials used in the thin film coating and the thicknesses of the alternating layers are chosen so that some wavelengths of incident visible light are more strongly reflected than are other wavelengths of incident visible light.

Additional objects and features of the invention will be made evident by the following description in which the preferred embodiments are set forth in detail in conjunction with the accompanying drawings.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention will be described in detail with reference to the accompanying drawings and examples. FIG. 1 shows a synthetic gemstone according to the present invention. The gemstone consists of a substrate 1 on which facets have been previously cut and polished, and an applied optical interference coating 2 over substantially the entire surface of substrate 1.

FIG. 2 shows a cross sectional detail of the surface of the synthetic gemstone of FIG. 1, showing the surface of the substrate 1 and the applied multilayer coating 2. The coating consists of alternating layers of a material of low refractive index 3, and a material of a high refractive index 4. The total number of layers in the coating 2 and the thicknesses of the individual layers are selected to provide the visual appearance desired for the gemstone.

The design and use of multilayer optical interference films to selectively reflect certain wavelengths of light are well known in the art; modern practices in design, use, and manufacture of such thin film optical filters are described, for example, in H.A. Macleod, *Thin Film Optical Filters* (Macmillan, New York, 1986). Using such practices, one of ordinary skill in the art can design and deposit on a surface multilayer thin film coatings that reflects some desired set of wavelengths of the incident visible light, and transmits the remaining wavelengths of the incident visible light. Although the design and performance of such multilayer films can in principle be calculated by hand, in practice specialized computer programs are used to determine the thicknesses of the layers in the coating and to predict the optical behavior of the optical coatings.

WO 96/06961

PCT/US95/10379

-6-

5 While it is desirable in the practice of the current invention that the optical coating be substantially uniform over the entire surface of the substrate, the optical coating can vary somewhat over the surface of the substrate without departing from the intent of the present invention, provided that the coating does not vary so much that some portions of the coating fail to reflect a portion of the incident visible light.

10 In the preferred embodiment of the invention the substrate and the optical thin film coating are composed of materials that are substantially transmissive to light (substantially free of absorption) over the wavelength range of 400 nanometers to 700 nanometers inclusive. However, substrates and coating materials that are moderately absorptive over this wavelength range may be used without departing from the intention of the present invention.

15 For example, the substrate may be composed of one or more materials chosen from the group consisting of: silicon dioxide, aluminum oxide, zirconium oxide, titanium oxide, hafnium oxide, germanium oxide, zinc oxide, scandium oxide, yttrium oxide, calcium oxide, magnesium oxide, barium oxide, beryllium oxide, boron oxide,  
20 phosphorus oxide, lead oxide, arsenic oxide, sodium oxide, potassium oxide and carbon, provided that the mixture as a whole is substantially non-absorbing in the range of 400 nanometers to 700 nanometers inclusive. Alternately, the substrate may be composed of various plastics (polymers based on carbon) provided that the plastic used is  
25 substantially non-absorbing in the range of 400 nanometers to 700 nanometers inclusive.

30 It will be evident to one of ordinary skill in the art that other types of materials not specified in the above description may also be suitable for practicing the present invention, provided that such materials are capable of being formed into a desired shape and are substantially non-absorbing in the range of 400 nanometers to 700 nanometers inclusive; substrates formed from such materials are intended to be within the scope of the present invention.

35 In the preferred embodiment of the invention the substrate should be formed of material with a relatively high refractive index, as this leads to a particularly pleasing visual appearance of the coated object. Particularly suitable substrate materials are therefore such materials



WO 96/06961

PCT/US95/10379

-7-

composed substantially of one or more members from the group consisting of: zirconium dioxide, titanium dioxide, silicon dioxide with a large percentage of lead oxide admixed, and carbon.

5 In the preferred embodiment of the invention the optical coating is deposited by a chemical vapor deposition process, and in particular by a low pressure chemical vapor deposition process (LPCVD). An LPCVD process is particularly suitable for practicing the present invention because it uniformly deposits an optical coating on all surfaces of even a complex shaped object. See SPIE Vol. 1168, pp 19-24 (1989).

10 Many other methods are known for the deposition of thin film optical coatings. See Thin Film Processes, J.L. Vossen and W. Kerns, Eds. (Academic Press, New York, 1978). For example, physical vapor deposition methods such as sputtering and electron beam evaporation, and plasma assisted methods such as plasma chemical vapor  
15 deposition, can be used to practice the present invention. In some cases it might be necessary with such coating methods to coat one set of surfaces of the substrate in one procedure, then rotate the substrate in a tooling fixture in order to allow deposition of the desired coating on the remaining surface(s) of the substrate. Any method which can  
20 be used to deposit a durable, well defined optical coating may be used to practice the current invention, provided that the method is capable of applying the thin film optical coating over at least 90% of the total surface of the substrate.

25 The present invention may be further understood by reference to the following examples.

#### EXAMPLE 1

30 A substrate composed of cubic zirconium dioxide and formed with cut and polished facets as in FIG. 1 was placed in a chamber and the chamber sealed. The atmosphere was exhausted from the chamber by means of a vacuum pump, and the chamber and substrate heated by external heaters to a temperature of about 500°C. Organometallic precursors capable of decomposing at 500°C to give thin films of silicon dioxide and tantalum pentoxide are alternately admitted to the  
35 chamber, each precursor being admitted in turn for a length of time sufficient to deposit the coating described by the following graphic representation of the coating: Substrate (HL)<sup>4</sup> H 1/2L, where each H

WO 96/06961

PCT/US95/10379

-8-

corresponds to a layer composed of tantalum pentoxide with a nominal thickness of 471 Ångstroms, and L corresponds to a layer composed of silicon dioxide with a nominal thickness of 715 Ångstroms.

5 When the deposition of the optical coating was complete, the chamber was cooled, air admitted, and the coated substrate removed. Visual examination showed that the coated substrate had a visual color of golden orange in transmission and blue in reflection. The perceived color was dependent on the angle of incidence of the illumination and the relative positions of the object and the viewer. A reflectance scan of a flat glass which was coated using the same procedure is shown in FIG. 3.

#### EXAMPLE 2

15 A substrate composed of lead crystal glass and formed in the shape of a turtle was placed in a chamber and the chamber sealed. The atmosphere was exhausted from the chamber by means of a vacuum pump, and the chamber and substrate heated by external heaters to a temperature of about 500°C. Organometallic precursors capable of decomposing at 500°C to give thin films of silicon dioxide and tantalum pentoxide are alternately admitted to the chamber, each precursor being admitted in turn for a length of time sufficient to deposit the coating described by the following graphic representation of the coating: Substrate (HL)<sup>4</sup> H 1/2L (1.7H 1.7L)<sup>4</sup> 1.7H 0.8L, where each H corresponds to a layer composed of tantalum pentoxide with a nominal thickness of 471 Ångstroms, and L corresponds to a layer composed of silicon dioxide with a nominal thickness of 632 Ångstroms. These layer thicknesses were chosen so as to provide a coating that would reflect the blue and red portions of the visible spectrum and transmit the green portion of the visible spectrum.

25 When the deposition of the optical coating was complete, the chamber was cooled, air admitted, and the coated substrate removed. Visual examination showed that the object produced had a visual color of green in transmission and silvery pink in reflection. The perceived color was dependent on the angle of incidence of the illumination and the relative positions of the object and the viewer. A reflectance scan of a flat glass which was coated using the same procedure is shown in FIG. 4.

**WO 96/06961****PCT/US95/10379****-9-**

**It is apparent from the foregoing discussion and examples that the present invention has provided a novel article of manufacture that is of great utility as a synthetic gemstone or decorative object.**

WO 96/06961

PCT/US95/10379

PATENT

-10-

What is claimed is:

1. An article of manufacture comprising a substantially transparent substrate of a size and shape suitable for use as a decorative object selected from the group consisting of gemstones and ornaments and a multilayer thin film interference coating over substantially the entire surface of said substrate, said coating consisting of alternating layers of substantially nonabsorbing materials with a relatively high refractive index and a relatively low refractive index with respect to each other, the thicknesses and identities of said layers being chosen so that the entire coating will preferentially reflect at least some of the incident light with wavelengths between 400 nanometers and 700 nanometers inclusive.
2. The article in claim 1 in which the substrate is a member selected from the group consisting of silicon dioxide, aluminum oxide, zirconium oxide, titanium oxide, hafnium oxide, germanium oxide, zinc oxide, scandium oxide, yttrium oxide, calcium oxide, magnesium oxide, barium oxide, beryllium oxide, boron oxide, phosphorus oxide, lead oxide, arsenic oxide, sodium oxide, potassium oxide and carbon.
3. The article in claim 1 in which the substrate is comprised of a polymeric material.
4. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are composed of metal oxides.
5. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating comprise materials selected from the group consisting of silicon dioxide, aluminum oxide, tantalum oxide, niobium oxide, titanium dioxide, hafnium dioxide, zirconium dioxide, magnesium fluoride, calcium fluoride, zinc sulfide, zinc selenide and carbon.
6. The article of claim 1 in which the number of layers comprising the multilayer thin film interference coating is three or greater.
7. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by a chemical vapor deposition process.

WO 96/06961

PCT/US95/10379

-11-

8. The article claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by a low pressure chemical vapor deposition process.

5 9. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by plasma assisted process.

10 10. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by a sputtering process.

11. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by an evaporative coating process.

15 12. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by dipping the substrate into liquid baths containing materials that decompose to form the desired layers.

20 13. The article of claim 1 in which the alternating layers comprising the multilayer thin film interference coating are sequentially deposited by spraying onto the surface of the substrate liquid solution containing materials capable of being decomposed to form the desired layers.

WO 96/06961

PCT/US95/10379

1/4




FIGURE 1

WO 96/06961

PCT/US95/10379

2/4




FIGURE 2

WO 96/06961

PCT/US95/10379

3/4




FIGURE 3



WO 96/06961

PCT/US95/10379

4/4




FIGURE 4

## INTERNATIONAL SEARCH REPORT

 Int. application No.  
PCT/US95/10379

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C30B 29/00; B32B 9/00; 19/00; A47G 35/00

US CL : 501/86; 63/62; 428/688, 689, 542.2, 411.1

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 501/86; 63/62; 428/688, 689, 542.2, 411.1

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 5,054,902 (KING), 08 October 1991, Abstract; column 3, lines 24-40.	1, 3-13
Y	E. HECTH, "OPTICS", published 1987 by Addison-Wesley Publishing Company, Inc., pages 376-377.	1-13
Y	US, A, 3,539,379 (MAYER) 10 November 1970, Abstract.	2



Further documents are listed in the continuation of Box C.



See patent family annex.

\*

Special categories of cited documents:

\*A\*

document defining the general state of the art which is not considered to be of particular relevance

\*E\*

earlier document published on or after the international filing date

\*L\*

document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\*

document referring to an oral disclosure, use, exhibition or other means

\*P\*

documents published prior to the international filing date but later than the priority date claimed

\*T\*

later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\*

document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\*

document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*A\*

document member of the same patent family

Date of the actual completion of the international search

16 SEPTEMBER 1995

Date of mailing of the international search report

26 OCT 1995

 Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

STEPHEN SAND

Telephone No. (703) 308-2351

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**